



SCIENTIFIC CONTROL LABORATORIES, INC.  
TESTING • CONSULTING

## TEST REPORT

Mr. Ed Wynn  
JDM Steel Service, Inc.  
330 E. Joe Orr Road, Unit 3  
Chicago Heights, IL 60411

**Lab No.:** 2010040223A  
**Inception:** Apr 15, 2010  
**Report Date:** Jun 03, 2010

**Test Type:** Salt Spray

### SAMPLE IDENTIFICATION:

Two (2) zinc phosphated and painted panels identified as "P&O" and "P&O Brushed".

### PROCEDURE:

The salt spray test was conducted in accordance with ASTM B 117. Creepage was evaluated per ASTM D 1654.

### RESULTS:

Hours	"P&O"	"P&O Brushed"
24	no corrosion	no corrosion
48	no corrosion	no corrosion
72	no corrosion	no corrosion
96	no corrosion	no corrosion
168	no corrosion	no corrosion
192	no corrosion	no corrosion
216	no corrosion	no corrosion
240	no corrosion	no corrosion
264	no corrosion	no corrosion
336	no corrosion	no corrosion
360	no corrosion	no corrosion

Note: It is our policy to keep copies of reports for six months. The data is kept on file for up to three years. Samples (if applicable) are kept for three weeks. Samples that are hazardous will be returned to the client. If this policy poses a difficulty, please contact us to make other arrangements. If reproduced, our report must be reproduced completely. Any unauthorized alteration of this report invalidates the content.



SCIENTIFIC CONTROL LABORATORIES, INC.  
TESTING • CONSULTING

JDM Steel Services  
Lab No.: 2010040223A  
June 3, 2010

Hours	"P&O"	"P&O Brushed"
<b>384</b>	no corrosion	no corrosion
<b>408</b>	no corrosion	no corrosion
<b>432</b>	no corrosion	no corrosion
<b>504</b>	no corrosion	no corrosion
<b>528</b>	no corrosion	no corrosion
<b>552</b>	no corrosion	no corrosion
<b>576</b>	no corrosion	no corrosion
<b>600</b>	no corrosion	no corrosion
<b>672</b>	no corrosion	no corrosion
<b>696</b>	no corrosion	no corrosion
<b>720</b>	no corrosion	no corrosion
<b>744</b>	no corrosion	no corrosion
<b>768</b>	no corrosion	no corrosion
<b>840</b>	no corrosion	no corrosion
<b>864</b>	no corrosion	no corrosion
<b>888</b>	no corrosion	no corrosion
<b>912</b>	no corrosion	no corrosion
<b>936</b>	no corrosion	no corrosion
<b>1032</b>	no corrosion no creepage	no corrosion no creepage

Note: It is our policy to keep copies of reports for six months. The data is kept on file for up to three years. Samples (if applicable) are kept for three weeks. Samples that are hazardous will be returned to the client. If this policy poses a difficulty, please contact us to make other arrangements. If reproduced, our report must be reproduced completely. Any unauthorized alteration of this report invalidates the content.



SCIENTIFIC CONTROL LABORATORIES, INC.  
TESTING • CONSULTING

JDM Steel Services  
Lab No.: 2010040223A  
June 3, 2010

Respectfully Submitted,

*Melanie M Williams*

Melanie Williams  
Metallurgical Services, Ext. 36  
mwilliams@sclweb.com

MW:mw

Note: It is our policy to keep copies of reports for six months. The data is kept on file for up to three years. Samples (if applicable) are kept for three weeks. Samples that are hazardous will be returned to the client. If this policy poses a difficulty, please contact us to make other arrangements. If reproduced, our report must be reproduced completely. Any unauthorized alteration of this report invalidates the content.